

## NOBLE POLYURETHANE WOOD CLEAR (4:1)

|                            |   |
|----------------------------|---|
| <b>PRODUCT DESCRIPTION</b> | Two pack, polyurethane based wood clear, with excellent water resistance. The dry film is having excellent adhesion to wooden surfaces. The product is recommended for interior and exterior applications, even in marine conditions. The dried film is transparent, non-yellowing and scratch resistance |
| <b>RECOMMENDED USES</b>    | Wooden surfaces for all architectural purposes, carpentry work, furniture etc.  |

### TECHNICAL DATA

|                                   |   |
|-----------------------------------|---|
| <b>COLOUR, DRY FILM</b>           | Clear   |
| <b>FINISH, DRY FILM</b>           | Smooth, Glossy / Semigloss                      |
| <b>VOLUME SOLIDS (ASTM D2697)</b> | 34 ± 2%   |
| <b>SPECIFIC GRAVITY</b>           | 0.99 ± 0.05 (Mixed)                             |
| <b>THEORETICAL SPREADING</b>      | 11 – 8.5 M <sup>2</sup> /LTR                    |
| <b>RECOMMENDED DFT (DRY FILM)</b> | 30 – 40 Microns/Coat (Minimum) depends on wood  |
| <b>RECOMMENDED WFT (WET FILM)</b> | 90 – 120 Microns/Coat (Minimum) depends on wood |
| <b>FLASH POINT</b>                | 25°C  |

### DRYING TIME

Drying time @ 30°C (Temperature, humidity, air movement, lm thickness and number of coats all affect the drying time.)

|                      |                 |
|----------------------|-----------------|
| <b>TOUCH DRY</b>     | 10 – 15 minutes |
| <b>DRY TO RECOAT</b> | 1 hour          |
| <b>HARD DRY</b>      | 24 hours        |

### ADVANTAGES

|   |  |
|---|--|
| <b>NOBLE POLYURETHANE WOOD CLEAR (4:1) SYSTEM</b> | Two pack system with long pot life, easy to apply, good coverage, excellent adhesion to wooden surfaces, excellent UV resistance properties. |
|---|--|



## NOBLE POLYURETHANE WOOD CLEAR (4:1)

### APPLICATION INSTRUCTION

|                            |   |
|----------------------------|---|
| <b>SURFACE PREPARATION</b> | Before application, the surface should be sound, clean and free from oil, grease, loose particles, dust, etc. Application can be done by the recommended application methods. |
|----------------------------|---|

### APPLICATION DATA

|                                 |   |
|---------------------------------|---|
| <b>APPLICATION METHOD</b>       | Conventional Spray or Auto spray  |
| <b>CLEANING/THINNING</b>        | Noble Polyurethane Thinner  |
| <b>THINNER (VOLUME)</b>         | 30 - 50% depending on method of applications                            |
| <b>CONV. SPRAY REQUIREMENTS</b> | Possible  |
| <b>MIXING RATIO (BY VOLUME)</b> | Base : Hardener<br>4:1 (Mix properly keep for 1015- minutes before use) |
| <b>POT LIFE @ 30°C (100 ml)</b> | 8 hours   |

### SYSTEM

|  |   |               |
|--|---|---------------|
| <b>RECOMMENDED SYSTEM</b><br>To be applied on prepared surface.<br>Apply on dry surface moisture less than 4%. | <b>For wooden surface:</b>                  |               |
|  | Noble Polyurethane Wood Sanding Sealer(4:1) | : 1 - 2 coats |
|  | Noble Polyurethane Wood Clear (4:1)         | : 1 - 2 coats |

### ADDITIONAL DATA

|                          |  |
|--------------------------|--|
| <b>SHELF LIFE @ 30°C</b> | 18 months, in original sealed container, with proper storage conditions. |
|--------------------------|--|



## NOBLE POLYURETHANE WOOD CLEAR (4:1)

### HEALTH & SAFETY

#### SAFETY PRECAUTIONS

As a general rule, avoid skin and eye contact by wearing overalls, gloves, goggles, and mask etc. Spillage on skin should immediately be removed by thorough washing with water and soap or suitable cleaner. Eye should be flushed with fresh water. Avoid inhalation of vapours and paint mist by wearing suitable mask. In the event of ingestion and eye contact, seek medical attention immediately. Painting must be carried out in well-ventilated area.

This product contains flammable materials and should be kept away from the sparks and open flames, smoking in the area should not be permitted. Local safety regulations should be followed.

### STORAGE & HANDLING

#### STORAGE

Store the paint in proper storage conditions as per the local regulations. Keep the paint container in sealed condition under shed, away from direct sunlight and extreme temperatures. Do not stock paint material near to any ignition sources. Do not put back the half or unused material back in original container, containing the supplied paint, to avoid contamination. Handle with care. Stir well before use.

**NOTE :** We warranty only the quality of our product and this data sheet is based on results obtained from experience and tests.  
We reserve the right to change data without prior notice. For surface preparation, safety details refer specifier and safety data.

This data sheet supersedes all previous issued.  
Issued: 0219

